



SOUND BC R8/18

GYPSUM PLASTERBOARD
DRYWALL CONSTRUCTION

Tech Specs

Dimensional tolerances		Type	SOUND BC R-8/18	
Thickness	+/- 0.5 mm	Reaction to fire	DI	EN 520
With	+0/-4 mm	Thermal Conductivity λ	A2-s1,d0 (B)	EN 520
Length	+0/-5 mm	W/(m.°C)	0.25	EN ISO 10456
		Density	kg/m ³	≥ 800
Application		Dimensions		
wall linings		Thickness	mm	12.5
		width	mm	1200
		Lengths	mm	2400
		Nominal Weight.		
		Board Thick. 12.5 mm	kg/m ²	9.4
		Breaking Loads		
		Thickness	12.5 mm	
		Longitudinal	≥550	
		Transversal	≥210	
		Acoustic Viel	white	
		Perforated area	14,3%	
		Perforated padron		
Ceilings		Dimensions (mm)		
Partitions		Square Edge - BC		



To maintain GYPFOR SOUND BC A R8/18 performance integrity, the drywall plasterboard should be protected from exposure to adverse conditions during storage and construction.